

Super Lube® "…everywhere and no wear"!



SYNCO CHEMICAL CORPORATION

24 DaVinci Drive, PO Box 405

Bohemia, NY 11716-0405

Phone (631) 567-5300, Fax (631) 567-5359

e-mail: info@super-lube.com

www.super-lube.com



COMPATIBILITY CHART

Super Lube® Super Kleen

Polymer (plastics) Constant Strain Tensile Testing	Rating
Acrylonitrile Butadiene Styrene (ABS)	E
Polyamide (PA) (Nylon)	E
Polyethylene (PE)	E
Linear Low-Density Polyethylene (LLDPE)	E
Crossed Linked Polyethylene (XLPE)	E
Chlorinated Polyethylene (CPE)	E
Low-Density Polyethylene (LDPE)	E
High Density Polyethylene (HDPE)	E
Medium Density Polyethylene (MDPE)	E
Polyvinylidene Flouride (PVDF)	E
*ultra high molecular mass (PE-UHMW)	E
*low density (PE-LD)	E
Polypropylene (PP)	E
Polyurethane (PUR)	E
Polyvinylchloride (PVC)	E
Thermoplastic High Heat-Resistant Nylon (THHN)	E
Thermoplastic elastomer (TPE)	E
Very Low Density Polyethylene (VLDPE)	E
Electrical Metal Tubing (EMT) (Metal)	E
Elastomer (rubber)	Rating
Acrylic rubber (ACM)	E
Buna S	E
Butyl (IIR)	E
Chlorosulfonated Polyethylene (CSPE)	E
Ethylene-propylene-diene rubber (EPDM)	E
Ethylene Propylene Rubber (EPR)	E
Natural rubber (NR)	E
Neoprene	E
Nitrile (NBR)	E
Polyurethane (AU, EU)	E
Styrene-butadiene rubber (SBR)	E
Viton (FKM)	E
RATING KEY	
E - Compatibility Excellent	
G - Compatibility Good	
NC - Not Compatible	