



Den Braven

Technical Data Sheet

Zwaluw FP PU Hand Foam

Fire resistant polyurethane foam certified according EN 1366-4



Product Description

Zwaluw FP PU Foam is an 1-component fire resistant insulation and construction foam developed to make a fire retardant seal between stony construction parts up till 240 minutes.

Benefits

- Fire retarding quality
- EN 1366-4 tested and approved
- Up till 240 minutes in combination with other products
- High quality professional PU Foam

Applications

Zwaluw FP PU Foam can be used in linear joints, according the EN 1366-4, in walls, ceilings and floor joints. In general Zwaluw FP PU Foam has an excellent adhesion on concrete, brick, stone, plaster, wood, metal and many plastics like polystyrene foam, rigid PU foam and uPVC.

Directions Of Use

Canister temperature: +5°C to +30°C (Recommended +15°C till +25°C). Application temperature (Environment and substrates): +5°C to +35°C. (Recommended +15°C till +25°C). When applying in cold conditions allow the canister to reach room temperature before use. Remove cap and screw the straw firmly onto the valve. Shake the canister vigorously prior to use at least 20 times. To apply foam, turn the canister upside down and press the adaptor. Half fill the cavity and, in case of low humidity, lightly spray the foam with water. The foam will expand to fill the rest. When fixing window frames, use spacers and wedges to hold the frame in place for approximately 24 hours until the foam is fully cured. Protect eyes and wear gloves and working clothes. Floor-covering and furniture to be covered with paper or plastic foil. Joints wider and deeper than 4 cm should be filled in multiple layers. Waiting time between applications 15-30

minutes. Before each application lightly spray with water. Only use in well ventilated areas. Store canister upright between +5°C and +25°C. Pressurized container! Protect from sunlight and do not expose to temperatures exceeding 50°C. Do not pierce or burn, even after use. Contains flammable propellants. Do not spray on a naked flame or any incandescent material. Keep away from sources of ignition. No smoking.

Additional information

Application temperature		+5°C to +35°C
Base		Polyurethane
Closed cells		± 70%
Curing time		100-120 minutes
Cutting time	FEICA TM1005	60-80 minutes
Density		20-30 kg/m ³
Fire behaviour	DIN 4102-1	B1
Tack free time	FEICA TM1014	10-15 minutes
Temperature resistance		-40°C to +90°C
Thermal conductivity		30-35 mW/m.K
Yield	FEICA TM1003	750 ml = 25-30 liter

These are typical values

Limitations

- Not suitable for continuous water immersion or use in enclosed spaces
- It will not bond to silicone, PTFE, polyethylene, polypropylene, soft plastics and greasy or oily surfaces

Surface Preparations and Finishing

Surfaces must be clean, free of oil and grease. Surfaces moisten slightly (spray) using a spray bottle. In cold temperatures, the foam at least one hour before use in warm to room temperature. Screws the can on a pistol with NBS thread. Shake the can vigorously before use (at least 30 times). Protect eyes and wear gloves and working clothes. Tapestry, floor-covering and furniture to be covered with paper or plastic foil. Fill about 50-60% of the joint, because the foam will expand. Fresh foam can be removed directly with



Den Braven

Bostik Benelux B.V.
Denariusstraat 11, 4903 RC Oosterhout
T +31 (0)162491000 | E info@denbraven.nl

15-04-2020
09:33:13
UTC



Den Braven

Technical Data Sheet

Zwaluw FP PU Hand Foam

Fire resistant polyurethane foam certified according EN 1366-4

Universal PU-Cleaner. After curing the surplus of the foam can be removed with a knife or spatula and the foam surface can be finished.

Paintability

Zwaluw FP PU Foam can be painted or coated with plaster or acrylic sealant.

Cleaning

Fresh foam can be removed directly with Zwaluw Universal PU-Cleaner. After curing the surplus of the foam can be removed with a knife or spatula and the foam surface can be finished.

Colour(s)

- Pink

Packaging

- Aerosol

For product specifications, please refer to the Product Detail Page

Shelf Life

If kept stored in a cool, dry place, in unopened original packaging, between +5°C and +25°C, shelf life is up to 18 months from production date. Store the canisters in an upright position.

Certifications

	EN 1366-4 FEICA member A+ French VOC Regulation Emicode EC1 Plus
--	---

Health & Safety

Product Safety Data Sheet must be read and understood before use. These are available on request and via the Den Braven websites.

Warranty & Guarantee

Den Braven warrants that its product complies, within its shelf life, to its specification.

Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Den Braven. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Den Braven's written consent. The technical information in this document serves as an indication and is non-exhaustive. Den Braven is not liable for any damage, either directly or indirectly, due to (editorial) errors, incompleteness and/or

incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Den Braven reserves the right to amend the wording of this document. Den Braven cannot be held liable for any damage, either directly or indirectly, due to the use of the product(s) depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage whatsoever. All deliveries are made exclusively in accordance with our general terms of conditions which have been filed at the Dutch Chamber of Commerce.

Better
results
through
Knowledge